



BROOKSIDE LABORATORIES, INC.
GEOTECHNICAL DIVISION
200 WHITE MOUNTAIN DRIVE
NEW BREMEN, OH 45869

**** PHYSICAL ANALYSIS REPORT ****

Brightview Golf Maintenance
Glendora, CA

File Number: 87359

Date Received/Started : 2/13/2023
Date Completed/Reported: 2/16/2023
Date Issued: 2/16/2023

Submitted By: Soil and Water Consulting

Lab Number	0241
Sample Description	TLC MATERIALS #20/30 SAND
Sample Condition	<u>XX</u> Normal ___ Other (see comments)

Method References

ASTM F1632
ASTM F1647 - Method A

D Values

** D10: 0.30
** D60: 0.70
** Coefficient of Uniformity: 2.34

*Reported values are an average of duplicated analysis

** NON A2LA ACCREDITED
* *This report may only be reproduced in its entirety.*
* *These results represent the sample submitted only.*



**** PHYSICAL ANALYSIS REPORT ****

Brightview Golf Maintenance
Glendora, CA

File Number : 87359
** Date of Analysis **
Start Date : 2/13/2023
Completed : 2/16/2023

Submitted By: Soil and Water Consulting Reviewed by:

Lab Number 0241
Sample Description TLC MATERIALS
#20/30
SAND

Particle Size Analysis

USGA Specs

Clay <.002mm	%	0.3	<= 3.0%
Silt .002mm - .05mm	%	1.7	<= 5.0%
Sand .05mm - 2.00mm	%	98.0	
Gravel > 2.0mm	%	0.0	

Org Mat 360 deg C (LOI) < 0.10

Sand Fractions

Sieve Size		% Retained		
#	mm			
10 -	2.0	Fine Gravel	0.0	2.0mm <= 3.0%
18 -	1.0	Very Coarse Sand	2.7	2.0mm + 1.0mm <= 10%
35 -	.500	Coarse Sand	62.9	
60 -	.250	Medium Sand	30.6	0.5mm + 0.25mm >= 60%
100 -	.150	Fine Sand	1.1	0.15mm <= 20%
140 -	.106	Very Fine Sand	0.4	0.106mm + 0.053mm <= 5.0%
270 -	.053	Very Fine Sand	0.3	