

	P.W. Gillibrand #30 Bag Sand(Palacio)	P.W. Gillibrand #30 Bag Sand(Calabasas)	P.W. Gillibrand #30 Sand(Angeles)	P.W. Gillibrand #30 Sand(Antelope)	TLC Materials #30 Sand(Glendor)	TLC Materials #30 Sand(Canyon Lakes)	TLC Materials #20/30 Sand(Eagle)	NorCal Sand, Inc. F-30 Kiln Sand(Madera)	Tacna USGA Sand(Yuma)
<b>Silt</b>	0.70	0.70	0.70	0.40	1.10	0.70	0.30	0.50	0.20
<b>Clay</b>	1.50	1.40	0.70	0.50	2.00	2.10	1.70	0.40	0.90
<b>Sand</b>	97.80	97.90	98.60	99.10	96.90	97.20	98.00	99.10	98.60
<b>Gravel</b>	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.30
<b>Organic Material</b>	0.10	<0.10	0.11	0.11	0.11	0.14	<0.1	<0.1	0.33
<b><u>Sieve #:</u></b>									
<b>Fine Gravel 10</b>	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.30
<b>Very Coarse Sand 18</b>	0.10	0.10	0.00	0.00	0.40	0.30	2.70	0.00	28.40
<b>Coarse Sand 35</b>	12.60	33.70	23.90	30.20	24.00	31.30	62.90	15.80	37.00
<b>Medium Sand 60</b>	83.40	63.20	53.50	67.30	70.60	63.00	30.60	73.30	29.20
<b>Fine Sand 100</b>	1.40	0.80	13.10	1.30	1.50	2.20	1.10	9.30	3.70
<b>Very Fine Sand 140</b>	0.20	0.10	6.50	0.20	0.20	0.30	0.40	0.60	0.20
<b>Very Fine Sand 270</b>	0.10	0.00	1.30	0.10	0.20	0.10	0.30	0.10	0.10
<b>Coefficient of Uniformity</b>	1.56	1.71	2.76	1.67	1.66	1.74	2.34	1.74	2.9